



## 4053 Closed Cell Sponge

Property	Test Method	Result
Polymer		Epichlorohydrin (ECH)
Color		Black
Sheet Size		36" x 46"
ASTM D-1056		2B3
ASTM D-6576-07 Classification		Type II, A or B, Medium
SAEJ18 APR2002		2B3
Density (lbs/ft <sup>3</sup> )	ASTM D 1056	18 ± 3
Durometer (Shore 00)	ASTM D 2240	60 ± 10
Compression Deflection (25%)	ASTM D 1056	11 ± 2
Compression Set (%)	ASTM D 1056	≤ 25%
Tensile Strength	ASTM D 412 (DIE A)	100 psi
Tear Strength (lb./in)	ASTM D 624 (DIE C)	20
Elongation (%)	ASTM D 412 (DIE A)	175%
Resilience	ASTM D 2362	35
Service Temperature:		
-Low	ASTM D 746	-40°F
-High Continuous	ASTM D 746	300°F
-High Intermittent	ASTM D 746	325°F
Water Absorption		
-Maximum Weight Change %	ASTM D 1056	< 5%
Fuel Immersion:		(7 days at 73.4°F)
ASTM Ref, Fuel B, Weight Change %	ASTM D 1056	< 50%
Accelerated Aging		(7 days at 158°F)
-Flexibility	ASTM D 1056	Pass
-Appearance Change	ASTM D 1056	None
-Change in Compression Deflection	ASTM D 1056	± 30%
Flammability	FMVSS302	Pass

Hanna Rubber Company  
 908 West 25<sup>th</sup> Street  
 Kansas City, Mo. 64108  
 P: 816-221-9600  
[www.hannarubber.com](http://www.hannarubber.com)