



6231 Closed Cell Sponge

Property	Test Method	Result
Polymer		NBR, PVC
Color		Natural
Sheet Size		48" x 68"
ASTM D-1056		2A2, 2B2, 2C2
ASTM D-6576-07 Classification		Type II, A, B, C, Soft, Med.
SAEJ18 APR2002		2A2, 2B2, 2C2
Density (lbs/ft ³)	ASTM D 1056	7 ± 2
Durometer (Shore 00)	ASTM D 2240	55 ± 5
Compression Deflection (25%)	ASTM D 1056	6 ± 2 psi
Compression Set (%)	ASTM D 1056	≤ 25%
Tensile Strength	ASTM D 412 (DIE A)	80 psi
Tear Strength (lb./in)	ASTM D 624 (DIE C)	17
Elongation (%)	ASTM D 412 (DIE A)	125%
Resilience	ASTM D 2362	7%
Service Temperature:		
-Low	ASTM D 746	-20°F
-High Continuous	ASTM D 746	160°F
-High Intermittent	ASTM D 746	220°F
Water Absorption		
-Maximum Weight Change %	ASTM D 1056	< 5%
Fuel Immersion: (%)		(7 days at 73.4°F)
ASTM Ref, Fuel B, Weight Change	ASTM D 1056	< 100%
Accelerated Aging		(7 days at 158°F)
-Flexibility	ASTM D 1056	Pass
-Appearance Change	ASTM D 1056	None
-Change in Compression Deflection	ASTM D 1056	± 30%
Flammability	FMVSS302	Pass

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.

Hanna Rubber Company
 908 West 25th Street
 Kansas City, Mo. 64108
 P: 816-221-9600
www.hannarubber.com