



NA 1076

Compressed Sheet with CR Binders

| Service Limits | | |
|-----------------------|----------------|-------------------------------------|
| Type | Description | Value |
| Temperature Limits | Maximum | 700°F (370°C) |
| | Continuous Max | 392°F (200°C) |
| Pressure Limits | Vacuum | 725 psi (50 bar) |
| ASTM F104 | Line call out | F712120-B4E99M9 |
| Color | | Black |
| Available sheet sizes | Thickness | 1/64", 1/32", 1/16", 3/32", 1/8" |
| | Sheet Sizes | 59" x 63" 59" x 126" |

| Typical Physical Properties | | |
|--|----------------------|--------------------------|
| Property | ASTM Test Method | Value |
| Density | | 106 lbs./ft ³ |
| Compressibility | F36 | 7 – 17% |
| Recovery | F36 | 46% |
| Tensile Strength across grain | F38 | 1740 psi |
| Creep relaxation | F38 | 20% |
| Thickness Increase after 5 hrs. immersion | F146 | |
| | ASTM IRM 903 @ 300°F | Max 30% |
| | ASTM Fuel B @ 77°F | Max 20% |
| Weight increase after 5 hrs. immersion | F136 | |
| | ASTM Fuel B @ 77°F | Max 20% |

Hanna Rubber Company
 908 West 25th Street
 Kansas City, Mo. 64108
 P: 816-221-9600
www.hannarubber.com