



NA 1092

Compressed Sheet with NBR Binders

Service Limits		
Type	Description	Value
Temperature Limits	Maximum	750°F (400°C)
	Continuous Max	518°F (270°C)
Pressure Limits	Maximum	1885 psi (130 bar)
	Continuous Max	1015 psi (50 bar)
ASTM F104	Line call out	F7713130E43M5
Color		Black
Available sheet sizes	Thickness	1/64", 1/32", 1/16", 3/32", 1/8"
	Sheet Sizes	59" x 63" 59" x 126"

Typical Physical Properties		
Property	ASTM Test Method	Value
Density		100 lbs./ft ³
Compressibility	F36	10 – 20%
Recovery	F36	Min 37%
Tensile Strength	F152	1740 psi
Thickness Increase after 5 hrs. immersion	F146	
	ASTM IRM 903 @ 300°F	Max 15%
	ASTM Fuel B @ 77°F	Max 15%
Weight increase after 5 hrs. immersion	F136	
	ASTM IRM 903 @ 300°F	Max 25%
	ASTM Fuel B @ 77°F	Max 30%

Hanna Rubber Company
 908 West 25th Street
 Kansas City, Mo. 64108
 P: 816-221-9600
www.hannarubber.com