



NA 1122

Compressed Sheet with NBR Binders

Service Limits		
Type	Description	Value
Temperature Limits	Maximum	1022°F (550°C)
	Continuous Max	806°F (430°C)
Pressure Limits	Maximum	2177 psi (150 bar)
	Continuous Max	1480 psi (102 bar)
ASTM F104	Line call out	F712290E33M4
Color		Black
Available sheet sizes	Thickness	1/64", 1/32", 1/16", 3/32", 1/8"
		Sheet Sizes

Typical Physical Properties		
Property	ASTM Test Method	Value
Density		91.14 lbs./ft ³
Compressibility	F36	12– 22%
Recovery	F36	Min 40%
Tensile Strength	F152	1305 psi
Thickness Increase after 5 hrs. immersion	F146	
	ASTM IRM 903 @ 300°F	Max 15%
	ASTM Fuel B @ 77°F	Max 15%
Weight increase after 5 hrs. immersion	F136	
	ASTM IRM 903 @ 300°F	Max 30%
	ASTM Fuel B @ 77°F	Max 20%
Torque Retention	(DIN 52913)	43 MPa

Hanna Rubber Company
 908 West 25th Street
 Kansas City, Mo. 64108
 P: 816-221-9600
www.hannarubber.com