



H45 Cork / Rubber

Property	Test Method	Result
Density	ASTM D3676	45.9lbs./ft ³ (0.74 g/cm ³)
Tensile Strength	ASTM F152	325 lbs./in ² (2240 kPa)
Compression @ 200psi	ASTM F36	27% (Recovery 95%)
Compression @ 400 psi		33% (Recovery 82%)
Shore "A" Hardness	ASTM D 2240	60 - 75
Flexibility	ASTM F147	3 max.
Fuel Immersion	ASTM F146	
Oil 1 (70 hrs. at 212°F)		-5 to +10%
Oil 3 (70 hrs. at 212°F)		-2 to +20%
Fuel A (22hrs. at 75°F)		-2 to +10%
Compression Set B	ASTM D395	80% max.
25% deflection, 22 hrs. at 158°F		
Temperature Range	ASTM D 2240	- 40 to 250°F (- 40 to 121°C)
Meets Specification	ASTM F104 F226000 M2 T	
	MIL-G-12803 P2255A	
	AMS-C-6183 (MIL-C-6183b) Type I or II, Cl 1, Gr B	
This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes		

Hanna Rubber accepts no responsibility for results obtained. Each user of these products, or information, should perform their own tests to determine the suitability of the material. Hanna Rubber does not guarantee that the user will obtain the same results. The data and information are subject to change without notice.

Hanna Rubber Company
 908 West 25th Street Kansas City, MO 64108
 P: 816-221-9600
www.hannarubber.com